

# Technical Data Sheet

## ProStab® T-181

Methyl tin stabilizer is an efficient stabilizer used in PVC hot working process. Its stability, transparency, compatibility and weather resistance are all superior to other organotin heat stabilizers. It is widely used in PVC sheet, panel, tubing and blow molding and injection molding products. It can also be used in food packaging, medicine packaging and non-toxic and harmless PVC products.

### Tech Spec

Items	Index
Appearance	Clear liquid
Tin content, %	≥19.20
Chrominance (Pt-Co)	≤50
Viscosity (25°C, Pa•S)	0.020-0.080
Specific gravity (ρ20°C)	1.17-1.19

### Hygiene and safety performance

According to the requirements of EU ROHS 2002/95/EC and follow-up revision, the content of cadmium, lead, mercury, hexavalent chromium, PBBs and PBDEs is not found (<MDL); according to US safety standard ASTM D3421-75 testing, 16 kinds of content of Phthalate are not found (<MDL).

### Recommended Dosage

PVC calendaring transparent hard sheet: 0.8-1.2phr

PVC thermal shrink package film and printing film: 1.2-1.6phr

PVC colloidal particle: 1.5-2.0phr

### Package and storage

220kg plastic /Iron drum or 1200kg IBC tank.

Storing the product in dry, well-ventilated and dark place. Keep the barrel mouth upward. Quality guarantee period is 12 months as from production date.



+86-536-8206760

[info@novistagroup.com](mailto:info@novistagroup.com)

[www.novistagroup.com](http://www.novistagroup.com)

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Novista Group and its subsidiaries. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patent.